

Washability and Reusability Statement

Product: Polypropylene Nonwoven (abrasive substrate) – Code **SABD8PB42B**

We hereby confirm that the SHALAG material **SABD8PB42B** has been evaluated for durability following multiple washing and drying cycles.

Laundrying: Samples were subjected to 0 (reference), 1, 5 and 10 domestic washing and drying cycles performed by **Shenkar Textile Testing Laboratory** in accordance with standard domestic laundrying conditions (ISO 6330 laundrying protocol confirmation available).

Post-laundrying evaluation: the material was evaluated after each stage, and the results demonstrate that:

- The material maintains its structural and mechanical integrity after repeated laundrying.
- Tensile strength remains within acceptable performance levels after up to 10 wash/dry cycles.
- No structural damage, tearing, or delamination/peeling of the abrasive side was observed in the evaluated samples.
- Minor changes in elongation and thickness are consistent with normal fibre relaxation after laundrying.



Conclusion

Based on testing, the nonwoven material maintains its mechanical integrity after repeated laundering and is suitable for reuse.

This statement summarizes the findings of Shalag Industries' test report dated 04 March 2026.

Omer Dorman
Director of R&D

This information is based on limited internal observations and is provided for general reference only. It does not constitute any warranty or representation of final performance or suitability. Use and reliance are at the recipient's own risk, and no liability of any kind is assumed or accepted.

info@shalag.com
www.shalag.com

Shalag Industries LTD
Kibbutz Shamir
Upper Galilee, 1213500 - **Israel**
Phone +972 4 6947856

Shalag US Inc
P.O. BOX 225, 917 SE Industry Drive
Oxford, North Carolina 27565, **USA**
Phone +1 919-690-0250

Shalag EU Spa
Via Livornese di Sopra, 82
Chiesina Uzzanese 51013 (PT) | **ITALY**
Phone +39 0572 48041



TESTING LABORATORY

TEST REPORT

Supplier's Name : Sycamore
Contact : Kathy Zeldich

Our No: 6-26

Identification and Information Received:

Blue Wipes – 25 x 20 cm - SABD8PB42B

Test requested:

Washing according to ISO 6330

Washing procedure: 5A 40°C.

Drying Procedure: T.D Low

Detergent: ECE non-phosphate detergent without optical brightener.

Number of washing and drying cycles: **1**

Date: 11 February , 2026

Signature: 

Shoshi Tfilin
Head of Textile Laboratories

**These results apply to samples
tested by our laboratory**

**The tested samples are
attached**



TESTING LABORATORY

TEST REPORT

Supplier's Name : Sycamore
Contact : Kathy Zeldich

Our No: 6-26

Identification and Information Received:

Blue Wipes – 25 x 20 cm - SABD8PB42B

Test requested:

Washing according to ISO 6330

Washing procedure: 5A 40°C.

Drying Procedure: T.D Low

Detergent: ECE non-phosphate detergent without optical brightener.

Number of washing and drying cycles: 5

Date: 11 February , 2026

Signature: 

Shoshi Tfilin
Head of Textile Laboratories

**These results apply to samples
tested by our laboratory**

**The tested samples are
attached**



TESTING LABORATORY

TEST REPORT

Supplier's Name : Sycamore
Contact : Kathy Zeldich

Our No: 6-26

Identification and Information Received:

Blue Wipes – 25 x 20 cm - SABD8PB42B

Test requested:

Washing according to ISO 6330

Washing procedure: 5A 40°C.

Drying Procedure: T.D Low

Detergent: ECE non-phosphate detergent without optical brightener.

Number of washing and drying cycles: **10**

Date: 11 February , 2026

Signature: _____


Shoshi Tfilin
Head of Textile Laboratories

**These results apply to samples
tested by our laboratory**

**The tested samples are
attached**