



# S41 SILICONE (COLOURS)

## PROFESSIONAL GRADE NEUTRAL SILICONE SEALANT

Date: 27 June 2022

Fact Sheet No.: TDS02195

### YOUR SMART ADVANTAGES

- Low modulus formulation with up to 25% movement capability.
- Excellent UV resistance and Weather resistant.
- Suitable for Interior and exterior use.
- Good for Window and door frames.

### USES

BOSTIK S41 SILICONE is a professional grade neutral cure silicone sealant, developed for window and door frame joints. Low modulus, UV resistance, weather resistant and low odour.

BOSTIK S41 SILICONE is specially developed for durable elastic sealing and provides strong adhesion to most plastics including PVCu and polycarbonate profiles and panels and gives excellent adhesion to both porous and non-porous substrates.

BOSTIK S41 SILICONE is resistant to cracking, shrinking, discolouration, UV radiation & temperature extremes. Making this sealant ideal for us in glazing applications that utilise polycarbonate sheeting, and for perimeter pointing of door and window frames.

Meeting the requirements of BS EN 15651:2017 – Parts 1 and 2 sealants for façade and glazing joints. BOSTIK S41 SILICONE is also a very low emission product certified to GEV-Emission EC1+ Level.

### PRODUCT CHARACTERISTICS

Colour	White, Anthracite and Brown
Form	Soft gunnable paste

Odour	Mild - Almost Odourless
Shore (A) hardness	20 approx.
Composition	2-pentanone Oxime - Unfilled
Product Code	30623109 White 310ml x 12
Supplied in PCR Cartridges.	30623106 Anthracite 310ml x 12
	30623105 Brown 310ml x 12
Storage/Shelf Life	Up to 12 months.*

### TYPICAL IN HOUSE PERFORMANCE DATA (Approx.)

100% modulus	0,35 N/mm <sup>2</sup>
Application rate	130 g/min
Application Temperature	+5°C to +40°C
Base	Silicone
Curing time	2-3 mm/24 hours
Density	1,22 g/ml
Elongation at break	550%
Flow	< 2 mm
Joint movement	25%
Skin formation	8 minutes @ +23°C/50% RH Always tool sealant within the given skin formation time frame

Temperature resistance	-40°C to +120°C
Tensile strength	1,3 N/mm <sup>2</sup>

## DIRECTIONS FOR USE

IMPORTANT: Before using BOSTIK S41 SILICONE refer to the relevant Health & Safety Data Sheet, available at [www.bostik.com/uk](http://www.bostik.com/uk)

## STORAGE CONDITIONS

\*Store for up to 24 months from Production date when stored in original, unopened packaging under cool, dry conditions within the temperature range +5°C to +25°C and out of direct sunlight. Protect from frost.

## PREPARATION

1. Work in warm but well ventilated conditions.
2. Ensure you have all necessary materials required.
3. Joint surfaces must be clean, dry, sound and free from dust, loose material and other contaminants that may impair adhesion.
4. If desired, place masking tape along the joint edges before application. This can make it easier to make a neat, tooled finish and not contaminate nearby surfaces. Use a spatula with a round end to tool the sealant and check that it fits into the gap between the masking tape so that it catches the excess sealant.
5. Do a test run without applying any sealant to 'get a feel' for the difficult areas to seal in corners, behind taps and raised joints.

## APPLICATION

1. Unscrew the nozzle, and using a sharp knife, carefully cut off the dome of the cartridge, taking care not to damage or shorten the thread. Screw the nozzle onto the cartridge.
2. Cut off the tapered end of the nozzle at a 45° angle, to a width matching the gap to be sealed.
3. Fit the cartridge into the cartridge gun by pressing the release plate and pulling out the plunger. Insert cartridge and repeatedly squeeze the trigger until the sealant appears.
4. Place the nozzle at the start of the gap, and gently squeeze the trigger. Push forward slowly, ensuring that contact is made by the sealant with both sides of the gap. At the end of the run, release the trigger and press the plunger release plate of the gun to stop the flow of material.
5. A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width.
6. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10mm is 1:1, with a minimum of 5 mm in width and depth.
7. For joints wider than 10 mm, the depth is the width divided by 3 plus 6 mm.
8. Within the working time of the product Smooth the sealant with a wet, round ended tool (do not use a wetted finger), remove any excess with a cloth moistened with white spirit and then remove the masking tape (if used) from either side of the bead.
9. If the application is in a damp or wet environment the sealant should be tooled to allow the water to run off the surface.
10. After use, ensure to wipe away any excess sealant from the nozzle. Replace the cap if appropriate.
11. The sealant skins over (approx. 8 minutes) and is fully cured in approx. 24 hours depending on bead width, temperature and humidity.

## CLEANING

### Uncured Sealant:

Excess uncured sealant should be removed carefully using a soft scraper. The remainder can be removed using a cloth just moistened with white spirit or soapy water. Repeat using another clean cloth moistened with white spirit or soapy water.

### Cured Sealant:

There is no adequate solvent; carefully cut away excess with a very sharp knife. Do not use solvent to remove product from skin – use soap and water.

### Regular Cleaning:

To maintain the appearance of the sealant regular cleaning should be undertaken.

## PAINTABILITY

This material is NOT paintable. We recommend covering the edges of the joint with masking tape to prevent adjacent surfaces that will be painted from being contaminated by silicone.

## PRECAUTIONS IN USE

BOSTIK S41 SILICONE cannot be applied to surfaces which are wet or have frost or ice on them. Will not resist abrasion in floor joints. Do not use in swimming pools. Do not use for aquarium applications. Prevent entry of uncured sealant into drains or watercourses. Do not use on or against bitumen. Not suitable for bedding double glazed/insulating glass units into frames without compatibility assessment. Not suitable for pedestrian walkways or sanitary applications.

Compatibility of the edge seals of insulation glass with sealants cannot be guaranteed by the supplier of the sealant, as the composition of the edge seals can be changed by the manufacturer without notice. Any advice on the compatibility of glazing sealants to the edge seals of insulation glass is based on experience and therefore not guaranteed.

Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates.

For any application not covered please contact Technical Services on +44 (0)1785 272625 or visit [www.bostik.com/uk](http://www.bostik.com/uk) for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instructions, first aid measures and spillage and disposal instructions see separate Health and Safety Data Sheet for BOSTIK S41 SILICONE, available at [www.bostik.com/uk](http://www.bostik.com/uk)

2538 <b>UK CA</b> 22	1213 <b>CE</b> 19
DOP available on: <a href="http://www.bostik.com/uk">www.bostik.com/uk</a> TDS Number: TDS02195  DoP nr: White: 645-22-3248 Anthracite: 645-22-3250 Brown: 645-22-3251	DOP available on: <a href="http://www.bostik.com/uk">www.bostik.com/uk</a> TDS Number: TDS02195  DoP nr: White: 645-22-3248 Anthracite: 645-22-3250 Brown: 645-22-3251
<b>EN 15651-1</b> F-EXT-INT-CC <b>EN 15651-2</b> G-CC	<b>EN 15651-1</b> F-EXT-INT-CC <b>EN 15651-2</b> G-CC
Façade & Glazing Sealant	Façade & Glazing Sealant

BOSTIK HOTLINE

Smart help +44 (0) 1785 272625



This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 0844 371 1192	<a href="mailto:customer.service@bostik.com">customer.service@bostik.com</a>
Technical Advice	Tel: 0844 371 1197	<a href="mailto:technical.service@bostik.com">technical.service@bostik.com</a>
Safety Data Sheets	Tel: 01785 272625	<a href="mailto:sds.box-eu@bostik.com">sds.box-eu@bostik.com</a>